

FLAMMABILITY TEST REPORT

Report No.: LEI17020001006A

Date Received: 09/02/17

Date Tested: 15/02/17

Date Issued: 16/02/17

Company Name & Address: ENGLISCH DEKOR
SCHEYDGASSE 29
AT-1210 WIEN

Contact Name: MANUELA SCHOPPER

Sample Details

Reference No.: Not stated
 Order No.: Not stated
 Style No.: Not stated
 Batch No.: Not stated
 Quality: Vintage Trend/Style
 Colour: Not stated
 Supplier: Not stated
 Intended Use: Upholstery
 Quoted Fibre Composition: 5 AF, 30 PES, 65 PVC
 Retailer: Not stated
 Buying Division: Not stated
 Sample Description: Red coloured woven fabric with grey coloured woven backing

Test Method	Pre Treatment	Requirement	Result
BS 5852: Part 1: 1979, Ignition source 0 (Cigarette)	Water soaked as clause 4.2 to 4.5 of BS 5651:1978 as modified by The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended) then line dried.	Compliance with Schedule 4 Part 1 (The cigarette test) of The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended).	Complies
Note: Fabric was submitted for test rather than the upholstery composite so as suggested by The Guide to the Furniture Regulations the cover fabric was tested for cigarette resistance using standard polyurethane foam (non-modified) as this will give the furniture manufacturer a good indication of its likelihood to pass the cigarette test for the finished article			
BS 5852: Part 1: 1979, Ignition source 1 (Match)	Water soaked as clause 4.2 to 4.5 of BS 5651:1978 as modified by The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended) then line dried.	Compliance with Schedule 5 Part 1 (The match test) of The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended).	Complies



STEVEN OWEN
(Chemical Technologist)

ANDREW HALLETT
(Flammability Team Leader)

CAROLE SPOWART
(Flammability Technician)

SIMON CHEE
(Operations Manager)

FLAMMABILITY TEST REPORT

Test Specification

Test Method: BS 5852: Part 1: 1979 as modified by Schedule 4 Part 1 & Schedule 5 Part 1 of The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended).

Ignition Source: Ignition source 0: Filterless cigarette
Ignition source 1: Butane Gas flowing at 45ml/min @ 25°C.

Flame Application Time: 20±1 seconds

Side Tested: Face

Filling Specification

Filling Type: Polyurethane foam

Supplier / Grade: Carpenter / RP21130 unmodified

Size: 450 X 300 X 75mm (back) & 450 X 150 X 75mm (seat)

Density / Hardness: 20-22 kg/m³ / Type B, 130N

Pre-treatment / Durability procedure

Water soaked as clause 4.2 to 4.5 of BS 5651:1978 as modified by The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended) then line dried.

Conditioning

Prior to Testing: At least 72 hours in ambient indoor conditions, then at least 16 hours in an atmosphere having a temperature of 20±5°C and a relative humidity of 50±20%

At Time of Testing: Temperature between 15°C & 30°C. Relative humidity between 20% & 70%

Test Results

"The following test results relate only to the ignitability of the combinations of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use."

Ignition source 0 (Test 1):	The cigarette burnt out within 29 minutes, there was no flaming or progressive smouldering. (Pass)
Ignition source 0 (Test 2):	The cigarette burnt out within 30 minutes, there was no flaming or progressive smouldering. (Pass)
Ignition source 1 (Test 1):	Flaming ceased with the removal of the burner, there was no progressive smouldering. (Pass)
Ignition source 1 (Test 2):	Flaming ceased with the removal of the burner, there was no progressive smouldering. (Pass)

Conclusions

The composite tested meets the requirements of Schedule 4 Part 1 (The cigarette test) of The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended). **PASS.**

The fabric tested meets the requirements of Schedule 5 Part 1 (The match test) of The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended). **PASS.**

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.