

FLAMMABILITY TEST REPORT

Report No.: LEI25051614A **Date Received:** 16/05/25 **Date Tested:** 22/05/25 **Date Issued:** 22/05/25
Original

Company Name & Address: ENGLISCH DEKOR HANDELS GMBH&CO KG
SCHEYDGASSE 29
1210 VIENNA
AUSTRIA

Contact Name: CHRISTINE JOST

Sample Details

Order No.: Not stated
Description: Upholstery FR “freiluft in-&outdoor”
Ref./Style No.: Not stated
Colour: A3785 – A3849
Quality: Upholstery FR “freiluft in-&outdoor”
Supplier: Not stated
Batch No.: Not stated
End Use: Not stated
No. Of Samples: Not stated
Quoted Fibre Composition: 60% PP, 40% PES FR
Weight / Width: 400g/m2
Retailer: General
Sample Description: Grey and brown coloured woven fabric with white coloured woven backing

Test Method	Pre Treatment	Requirement	Result
BS 5852:2006 Clause 11 (upholstery composite) Ignition source 5	Watersoak as Annex E of BS 5852: 2006	As BS 5852:2006 Clause 11 (upholstery composite) Ignition source 5	NI/5 (PASS)

.....
STEVEN OWEN
(Technical, Quality &
Systems Director)

.....

ANDREW HALLETT
(Flammability Team Leader)

.....
CAROLE SPOWART
(Flammability
Administrator)

.....
TREFOR LEE
(Senior Flammability
Technician)

Report No.: LEI25051614A Original Page 1 of 3

FLAMMABILITY TEST REPORT

Test Specification

Test Method: BS 5852:2006 Clause 11 (upholstery composite) Ignition source 5

Uncertainty of Measurement

The uncertainty of measurement has been estimated to be 5.99%

Foam specification

Supplier / Grade: Carpenter / RX36110
Size: 450 x 450 x 75mm (back) & 450 x 300 x 75mm (seat)
Density / Hardness: 36kg/m³ ± 5% / 105N ± 15%

Conditioning

Prior to Testing: At least 72 hours in ambient indoor conditions, then at least 24 hours in an atmosphere having a temperature of 23 ± 2°C and a relative humidity of 50 ± 5%

At Time of Testing: Temperature of 10 °C to 30 °C and a relative humidity of 15 % to 80 %

Test Results

"The following test results relate only to the ignitability of the combination of upholstery composites (BS 5852: 2006, Clause 11) under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use";

Test number / position	1	2
Criterion of Ignition		
Smouldering Criteria		
Externally detectable amounts of smoke, heat or glowing 60 minutes after crib ignition	No	No
Escalating smouldering behaviour rendered the test unsafe to continue and required forcible extinction	No	No
Smouldering essentially consumed the test specimen within the duration of the test / Smouldering reached the extremities of the test specimen (Other than the top of the vertical part of the test specimen) within the duration of the test	No	No
Flaming Failure		
The test specimen continued to flame for more than 10 minutes after the ignition of the crib	No	No
Escalating combustion behaviour rendered the test unsafe to continue and required forcible extinction	No	No
Flaming essentially consumed the test specimen within the duration of the test	No	No
Flaming reached the extremities of the test specimen (Other than the top of the vertical part of the test specimen) within the duration of the test	No	No
Debris from the test specimen caused an isolated floor fire that continued to flame for more than 10 minutes after the ignition of the crib	No	No
Final Examination		
Progressive smouldering was observed when the sample was dismantled	No	No
Evidence of charring within the filling (other than discolouration) more than 100mm in any direction, apart from upwards, from the nearest part of the original position of the ignition source	No	No
Time to extinction of flames after crib ignition	3 Minutes 48 Seconds	4 Minutes 55 Seconds
Time to extinction of glowing after crib ignition	Due to the amount of smoke in the test enclosure it was not possible to see when crib glow ceased.	Due to the amount of smoke in the test enclosure it was not possible to see when crib glow ceased.
Time to extinction of smoke after crib ignition	Due to the amount of smoke in the test enclosure it was not possible to see when smoking ceased.	Due to the amount of smoke in the test enclosure it was not possible to see when smoking ceased.
Maximum extent of damage to back (mm) Length / Width	400 222	400 273
Maximum extent of damage to base (mm) Length / Width	130 215	148 260
Test Result	NI/5 (PASS)	NI/5 (PASS)
Ignitability performance index: "Clause 11 - NI/5"		

FLAMMABILITY TEST REPORT

The client acknowledges and agrees that any services provided and/or reports produced by Intertek are done so within the limits of the scope of work agreed pursuant to the client's specific instructions. This report relates specifically to the sample(s) tested that were drawn and delivered by the client or their nominated third party. Intertek does not make any representation or warranty for any bulk samples or certify the bulk samples received from the client. Furthermore, Intertek does not provide a warranty or verification on the sample(s) representing any specific goods, material and/or shipment and only relate to the sample(s) as received and tested. Intertek have aimed to conduct the review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. In no event, will the contents of any reports or any extracts, excerpts or parts of any reports be distributed or published without the prior written consent of Intertek in each instance. Only the client is authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.

The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor of $k = 2$, providing a level of confidence of approximately 95 %. Unless otherwise specified all compliance and pass/fail statements are binary simple acceptance based on the tolerance interval and, with the exception of graded methods, a test uncertainty ratio greater (TUR) than 4:1. For graded methods the TUR will drop to as low as 0.5:1 when the tolerance limits are within a grade division of the upper scale limit. The Uncertainty budgets are stated for each Test method, these are for reference, and should be considered when results are on or close to Specification Limits / Requirements and in such cases it should be noted that the risk of false acceptance or rejection may be as high as 50%, for further information please refer to ILAC G8.