



LANARTEX S.r.l.

Via I Maggio, 27
59013 Oste - Montemurlo (PO)
Tel.: 0574-071701 Fax: 0574-899903
E-mail: labo@lanartex.it
www.lanartex.it



MESSRS:

ENGLISH DEKOR HANDELSGMBH & CO KG

SCHEYDGASSE 29
1210 WIEN (AUSTRIA)
AT

REPORT NR

260005075-001

REPORT DATE

31/07/2026

ACCEPTANCE DATE

20/07/2026

START TEST DATE

24/07/2026

END TEST DATE

24/07/2026

SAMPLING BY CUSTOMER

TEST REPORT

Item Name: ART. SMARTEX

Material type: Orthogonal fabric

Intended use: Upholstery

Weight: 0.00 g/m²

Thickness: 2.50 mm



Technical Manager

Dott.ssa Guidotti Valentina

Manager Director

Patrizia Rosati

(*) = Tests and analytes marked with asterisk are not accredited ACCREDIA. The content of the present document refers **exclusively to the submitted samples** and not to the batch that they want to represent. This report is made solely on the basis of materials supplied by the customer. This test report cannot be reproduced in part without written permission of LANARTEX. The sample description content is under the full responsibility of the customer and not of the laboratory. Except when specifically stated, **the results apply to the sample as received**. For any further information, please read the General Sales Condition on the Lanartex website.



LANARTEX S.r.l.

Via I Maggio, 27
59013 Oste - Montemurlo (PO)
Tel.: 0574-071701 Fax: 0574-899903
E-mail: labo@lanartex.it
www.lanartex.it



REPORT NR
REPORT DATE

260005075-001
31/07/2026

TEST LIST

TEST

METHOD

ACCREDIA

Flammability of fabrics - Upholstered furniture

Infiammabilità dei tessuti - Mobili imbottiti

UNI 9175:2010 + UNI 9176:2010

(*) = Tests and analytes marked with asterisk are not accredited ACCREDIA. The content of the present document refers **exclusively to the submitted samples** and not to the batch that they want to represent. This report is made solely on the basis of materials supplied by the customer. This test report cannot be reproduced in part without written permission of LANARTEX. The sample description content is under the full responsibility of the customer and not of the laboratory. Except when specifically stated, **the results apply to the sample as received**. For any further information, please read the General Sales Condition on the Lanartex website.

**LANARTEX S.r.l.**

Via I Maggio, 27
59013 Oste - Montemurlo (PO)
Tel.: 0574-071701 Fax: 0574-899903
E-mail: labo@lanartex.it
www.lanartex.it



REPORT NR
REPORT DATE

260005075-001
31/07/2026

RESULTS

M.U.		RESULT
UNI 9175:2010 + UNI 9176:2010		
Flammability of fabrics - Upholstered furniture		
<i>Infiammabilità dei tessuti - Mobili imbottiti</i>		
Pretreatment (according to UNI 9176)		You submit samples of the test material to 200 steps of a brush with weight 15 ± 1 g/cm ² of the apparent surface of contact between the brush and the same sample
<i>Pretrattamento (secondo UNI 9176)</i>		<i>Si sottopongono i campioni di materiale in esame a 200 passaggi di una spazzola con peso di 15 ± 1 g/cm² della superficie apparente di contatto tra la spazzola stessa e il campione</i>
Kind of sample		Cover material
<i>Tipo campione</i>		<i>Tessuto esterno</i>
Filling material		PU FR HR30S (30-33 Kg/m ³) SS20 supplied by the laboratory
<i>Materiale per imbottitura</i>		<i>PU FR HR30S (30-33 Kg/m³) SS20 fornito dal laboratorio</i>
Presence of combustion in non visible parts		No
<i>Presenza di combustione nelle parti non a vista</i>		No
Test assembly 1		Sample obtained with long side parallel to the longitudinal direction of the covering + filling material
<i>Assemblaggio 1</i>		<i>Campione ricavato con lato lungo parallelo alla direzione longitudinale del rivestimento + imbottitura</i>
Test assembly 2		Sample obtained with long side parallel to the transversal direction of the covering + filling material
<i>Assemblaggio 2</i>		<i>Campione ricavato con lato lungo parallelo alla direzione trasversale del rivestimento + imbottitura</i>
Preliminary test on filling material - 20 s - Result 1		Positive
<i>Esame preliminare su imbottitura - 20 s - Risultato 1</i>		<i>Positivo</i>
Preliminary test on filling material - 20 s - Result 2		Positive
<i>Esame preliminare su imbottitura - 20 s - Risultato 2</i>		<i>Positivo</i>
Time post-combustion flame @ 20s (Test assembly 1 to 3)		0
<i>Tempo di post-combustione con fiamma @ 20s (Assemblaggi 1-2-3)</i>		[0; 0]
Time of post-glow @ 20s (Test assembly 1 to 3)		21
<i>Tempo di Post-incandescenza @ 20s (Assemblaggi 1-2-3)</i>		[19; 22]
Test assembly numbers with Positive results @ 20s		1-2
<i>Identificativo degli assemblaggi con risultato Positivo @ 20s</i>		
Time post-combustion flame @ 80s (Test assembly 1 to 3)		1
<i>Tempo di post-combustione con fiamma @ 80s (Assemblaggi 1-2-3)</i>		[1; 1]

(*) = Tests and analytes marked with asterisk are not accredited ACCREDIA. The content of the present document refers **exclusively to the submitted samples** and not to the batch that they want to represent. This report is made solely on the basis of materials supplied by the customer. This test report cannot be reproduced in part without written permission of LANARTEX. The sample description content is under the full responsibility of the customer and not of the laboratory. Except when specifically stated, **the results apply to the sample as received**. For any further information, please read the General Sales Condition on the Lanartex website.

**LANARTEX S.r.l.**

Via I Maggio, 27
59013 Oste - Montemurlo (PO)
Tel.: 0574-071701 Fax: 0574-899903
E-mail: labo@lanartex.it
www.lanartex.it



REPORT NR
REPORT DATE

260005075-001
31/07/2026

Time of post-glow @ 80s (Test assembly 1 to 3)

Tempo di Post-incandescenza @ 80s (Assemblaggi 1-2-3)

S

47

[45; 49]

Test assembly numbers with Positive results @ 80s

Identificativo degli assemblaggi con risultato Positivo @ 80s

ID

1-2

Time post-combustion flame @ 140s (Test assembly 1 to 3)

Tempo di post-combustione con fiamma @ 140s (Assemblaggi 1-2-3)

S

2

[2; 1]

Time of post-glow @ 140s (Test assembly 1 to 3)

Tempo di Post-incandescenza @ 140s (Assemblaggi 1-2-3)

S

51

[49; 52]

Test assembly numbers with Positive results @ 140s

Identificativo degli assemblaggi con risultato Positivo @ 140s

ID

1-2

Classification achieved

Classificazione raggiunta

11M

11M

NOTES

The results of the following test concern only flammability characteristics of the combination of materials they constitute upholstered furniture according to the particular conditions used in the test must therefore not be used as hazard assessments potential fire of materials or products, in their intended use. Conditioning times: Cover at least 48 hrs at 23±2 °C and 50±5 R.H. % and Filling from 72 to 74h at 80±5 °C and 80±5 R.H. % followed by at least 48 hrs at 23±2 °C and 50±5 R.H. %. The laboratory is not liable for any deviation of the results caused by the failure to declare the test information requested from the customer. Sampling by the customer.

Disclaimer: Any average values reported in this test report are for information purposes only. For the assessment of compliance and material classification, only the results of the individual test sets shall be considered valid, in accordance with the requirements of the reference standard.

I risultati della seguente prova riguardano esclusivamente caratteristiche di infiammabilità della combinazione di materiali che costituiscono mobili imbottiti secondo le particolari condizioni usate nella prova, non devono quindi essere utilizzati come valutazioni della pericolosità d'incendio potenziale dei materiali o dei prodotti, nella loro destinazione d'uso. Periodi di condizionamento: Rivestimento almeno 48 ore con temperatura di 23±2 °C e U.R. di 50±5 % e imbottitura: da 72 a 74h con temperatura di 80±5 °C e umidità relativa di 80±5 % seguito da almeno 48 ore con temperatura di 23±2 °C e umidità relativa di 50±5 %. Il laboratorio non risponde per eventuali scostamenti dei risultati causati dalla mancata dichiarazione delle informazioni di prova richieste al cliente. Modalità di campionamento a cura del cliente.

Disclaimer: Gli eventuali valori medi riportati nel presente rapporto hanno valenza puramente informativa. Ai fini della valutazione della conformità e della classificazione del materiale, fanno fede esclusivamente i risultati ottenuti dai singoli set di prova, come previsto dalle specifiche della norma di riferimento.

END OF REPORT