



LANARTEX S.r.l.

Via I Maggio, 27
59013 Oste - Montemurlo (PO)
Tel.: 0574-071701 Fax: 0574-899903
E-mail: labo@lanartex.it
www.lanartex.it



LAB N° 0572 L

MESSRS:

ENGLISH DEKOR HANDELSGBH & CO KG

SCHEYDGASSE 29
1210 WIEN (AUSTRIA)
AT

REPORT NR

220007383-001

REPORT DATE

21/11/2022

ACCEPTANCE DATE

16/11/2022

START TEST DATE

21/11/2022

END TEST DATE

21/11/2022

SAMPLING BY CUSTOMER

TEST REPORT

Item Name: ART. AQUATEX UNI III

Material type: Orthogonal fabric

Intended use: Upholstery



Technical Manager

Dott.ssa Guidotti Valentina

Manager Director

Patrizia Rosati

(*) = Tests and analytes marked with asterisk are not accredited ACCREDIA. The content of the present document refers **exclusively to the submitted samples** and not to the batch that they want to represent. This report is made solely on the basis of materials supplied by the customer. This test report cannot be reproduced in part without written permission of LANARTEX. The sample description content is under the full responsibility of the customer and not of the laboratory. Except when specifically stated, **the results apply to the sample as received**. For any further information, please read the General Sales Condition on the Lanartex website.



LANARTEX S.r.l.

Via I Maggio, 27
59013 Oste - Montemurlo (PO)
Tel.: 0574-071701 Fax: 0574-899903

E-mail: labo@lanartex.it
www.lanartex.it



LAB N° 0572 L

REPORT NR
REPORT DATE

220007383-001
21/11/2022

TEST LIST

TEST	METHOD	ACCREDIA
Colour fastness - Chlorinated water <i>Solidità delle tinte - Acqua clorata</i>	UNI EN ISO 105 E03:2010	
Colour fastness - Bleaching: Hypochlorite <i>Solidità delle tinte - Sbianca: Ipoclorito</i>	UNI EN 20105 N01:1997	*

(*) = Tests and analytes marked with asterisk are not accredited ACCREDIA. The content of the present document refers **exclusively to the submitted samples** and not to the batch that they want to represent. This report is made solely on the basis of materials supplied by the customer. This test report cannot be reproduced in part without written permission of LANARTEX. The sample description content is under the full responsibility of the customer and not of the laboratory. Except when specifically stated, **the results apply to the sample as received**. For any further information, please read the General Sales Condition on the Lanartex website.



LANARTEX S.r.l.

Via I Maggio, 27
59013 Oste - Montemurlo (PO)
Tel.: 0574-071701 Fax: 0574-899903

E-mail: labo@lanartex.it
www.lanartex.it



LAB N° 0572 L

REPORT NR
REPORT DATE

220007383-001
21/11/2022

RESULTS

	M.U.	RESULT
UNI EN ISO 105 E03:2010		
Colour fastness - Chlorinated water		
<i>Solidità delle tinte - Acqua clorata</i>		

pH test solution		8
<i>pH soluzione di prova</i>		
Cl₂ active	mg/l	100
<i>Cl₂ attivo</i>		
Colour change	Grado	4-5
<i>Cambio di tono</i>		

NOTES

Evaluation with grey scale for colour change ISO 105 A02.

Valutazione con scale dei grigi per il cambiamento di tono ISO 105 A02.

	M.U.	RESULT
UNI EN 20105 N01:1997		
Colour fastness - Bleaching: Hypochlorite		
<i>Solidità delle tinte - Sbianca: Ipoclorito</i>		

Colour change	Grado	4-5
<i>Cambio di tono</i>		

NOTES

Evaluation with grey scale for colour change ISO 105 A02; pH of test solution: 11±0,2.

Valutazione con scale dei grigi per il cambiamento di tono ISO 105 A02; pH soluzione di prova: 11±0,2.

END OF REPORT

(*) = Tests and analytes marked with asterisk are not accredited ACCREDIA. The content of the present document refers **exclusively to the submitted samples** and not to the batch that they want to represent. This report is made solely on the basis of materials supplied by the customer. This test report cannot be reproduced in part without written permission of LANARTEX. The sample description content is under the full responsibility of the customer and not of the laboratory. Except when specifically stated, **the results apply to the sample as received**. For any further information, please read the General Sales Condition on the Lanartex website.