



Report VN735 131527.1 Test Report

Applicant

ENGLISCH DEKOR HandelsGmbH & CoKG
Scheydgasse 29
1210-Wien
Austria

Reference

Manuela Schopper

Application

Determination of abrasion resistance according to EN ISO 5470-2.

Test material

"canvas"

Material used in testing was anonymized for laboratory purposes. A detailed sample list is contained in the report.

Issuing and Signatures

Number of pages contained: 4
Original Issue / Vienna 28.07.2017 / AA / 188
Translation

Authorised for Institute
Ing. Hannes Vittek

i.V. Zauböck

Contents

1	Order	2
1.1	Chronology	2
1.2	Samples	2
2	Findings / Tests performed	2
2.1	Description of the specimen	2
2.3	Determination of abrasion resistance of rubber- or plastics-coated fabrics	3
3	Remarks	4

1 Order

1.1 Chronology

Date	Received	Order
14.07.2017	17.07.2017	Determination of abrasion resistance according to EN ISO 5470-2.

1.2 Samples

Nr.	Received	Sample Identification
1	17.07.2017	"canvas"

(Unless otherwise stated samples are provided by the customer.)

2 Findings / Tests performed

2.1 Description of the specimen

Description of the specimen according to DIN 60 000

Test results

Tested sample: 1

Material composition (declaration by the applicant)	Coating: 100% PVC
Technological description	Coated (embossed) knitted fabric with an intermediate foam layer

2.3 Determination of abrasion resistance of rubber- or plastics-coated fabrics

Test conditions

According to EN ISO 5470 part 2

Method: method 2, dry

Used abrasion material: Silicon carbide, grain P180

Abrasion load: 795g (corresponds 12 kPa)

Note: The evaluation was appropriate according EN 15618 for the respective performance category of the defined number of abrasion-turns. (300 T., 500 T. and 700 T.)

Test results

Tested sample: 1

Number of abrasion-turns	Evaluation of damage of the sample			
	specimen 1	specimen 2	specimen 3	specimen 4
100	1	1	1	1
200	1	1	1	1
300	1	1	1	1
500	1-2	1-2	1-2	1-2
700	2	2	2	2

Scale for evaluation of the damage:

0	None	No change of surface.
1	very mild	Change of gloss. No print abrasion (if present). No attack of surface coating.
2	mild	Change of colour. Print (if present) is partly or completely abraded. The surface coating was not attacked or only mild superficial.
3	moderate	The surface coating was attacked.
4	heavy	The surface coating is worn and the interlayer or the foam layer was attacked.
5	completely destroyed	The basic fabric appears.

Evaluation according to EN 15618

Number of abrasion-turns without exposition of the interlayer under the top layer:

≥ 700 turns

3 Remarks

Validity

There are no regulations concerning duration of validity in the individual test standards. As the results of the examinations refer only to the submitted and examined samples, the report is valid for these for an unlimited period. A period of validity specified as part of an expert evaluation is in the discretion of the consultant or the ÖTI.

The applicability of results and expert evaluations for materials not tested is in the responsibility of the applicant. Whereby an apportionment of results as well as any specified period of validity can only be done for identically constructed products and only as long as the product produced unchanged.

Possible national or international restrictions concerning the terms of usability of test and classification reports have to be considered; this is not the responsibility of the test laboratory.

Sample Material

Results of performed tests only refer to the sample material provided.

Without explicit written other agreement testing is destructive and the sample material is transferred to the property of ÖTI, which is entitled to freely decide on storage and disposal.

Issuance

The valid first issue is done in paper and has single-handed signatures. For reference purposes and filing an unsigned electronic duplicate can be delivered in pdf format. Duplicates and translations will be marked accordingly on the cover sheet.

Quality management, Accreditation and Notification

All tests and services are performed under a quality management system according to EN ISO/IEC 17025 respectively EN ISO/IEC 17065.

The ÖTI is accredited as Testing Laboratory and Certification Body for products. It also is a Notified Body for several directives with the registration number 0534 (see <http://ec.europa.eu/enterprise/newapproach/nando/>). Accreditation as Testing Laboratory was provided by Akkreditierung Austria (bmwfw). The scope of accreditation is listed on www.bmwfw.gv.at/akkreditierung.

According to the decree on the use of the accreditation mark ("AkkZV") the accreditation mark is only to be used by the accredited Conformity Assessment Body.

Application of the registration number of the Notified Body: As to personal protective equipment (PPE) the requirements of PSA-SV § 10, BGBl. Nr. 596/1994 as amended and article 13 of the Directive 89/686/EEC have to be kept. With construction products the application is only permitted within the declaration of performance for CE-marking.

Copyright and Usage Notes

It is pointed out, that any alterations, amendments or falsifications of reports not authorized by the issuer of the report will be prosecuted as civil and criminal offences; this especially to the appropriate requirements of ABGB, UrhG, UWG and criminal law and their respective international equivalents.

Reports are protected under international copyright laws. Written consent of the ÖTI is required for publications (also in excerpt) and reference to tests for public relation purposes. Reports may only be reproduced in full length.

End of report