

Test Report No.:	2307531-001	
Date Test Report	24-nov-23	Customer Code 08077
Acceptance:	2307531	Dear:
Arrival date sample	13-nov-23	ENGLISH DEKOR HANDELSGMBH & CO KG
Start date test	13-nov-23	Scheydgasse 29
End date test	23-nov-23	1210 WIEN AUSTRIA
References:	packing list 15849 del 8/11/23	C.a. sig. Luiz Lange
Sampling Mode:	Sampling by Customer *	Phone:
[C] Item: ART. FEEL [C] Declared Composition: 100% Polyester [C] End use: furnishing [C] Typology: fabric [C] Note: FR treated fabric Return: no requested		

Test Results

Test	Method	U.M.	Result
15086 WATER SOAKING	BS 5852:2006 - Annex E		.
Start date test	21/11/2023		
End date test	22/11/2023		
Instrument:	Flat-bottomed dish		
PROCEDURE: The sample has been submitted to the following procedure: using a liquor ratio of 1:20 the specimen has been immersed in water with a degree of hardness of 8 dH to 10 dH, containing 0.5 g/l of non-ionic wetting agent, at an initial temperature of 40 °C, for 30 minutes. Then the specimen has been rinsed in water with the same hardness, using a liquor ratio of 1:20 for 2 minutes and then dried.			
AFTER CONDITIONING, THE SPECIMEN WILL BE SUBMITTED TO FIRE TESTS, AS DESCRIBED BELOW.			
15066 UPHOLSTERY FURNITURE	UNI EN 1021-1:2014		.
COMPONENTS: ASSESSMENT OF THE IGNITABILITY BY SMOULDERING CIGARETTE			
Start date test	22/11/2023		
End date test	23/11/2023		
Instrument:	Small Test Rig and burner		
Test carried out on			Cover fabric
Pretreatment carried out			sample was subjected to a water soak, as above described
Ignition source			source 0 (SMOULDERING CIGARETTE)

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 003900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com



LAB N° 0045 L

Test Report No.: **2307531-001**

Test	Method	U.M.	Result
TEST RESULT			SAMPLE PASSES THE TEST: NON IGNITION
Note: to assess the ignitability of this sample, the test has been carried out using a fire-retardant polyurethane foam with a density of 35 kg/m ³ as filling of the upholstered seating. The test result could be different using another type of filling material.			
Deviations from the method			None
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			
15076 UPHOLSTERY FURNITURE:	UNI EN 1021-2:2014		.
ASSESSMENT OF THE IGNITABILITY BY MATCH FLAME			
Start date test	22/11/2023		
End date test	23/11/2023		
Instrument: Small Test Rig and burner			
Test carried out on			Cover fabric
Pretreatment carried out			sample was subjected to a water soak, as above described
Ignition source			source 1 (MATCH FLAME EQUIVALENT)
TEST RESULT			SAMPLE PASSES THE TEST: NON IGNITION
Note: to assess the ignitability of this sample, the test has been carried out using a fire-retardant polyurethane foam with a density of 35 kg/m ³ as filling of the upholstered seating. The test result could be different using another type of filling material.			
Deviations from the method			None
Annex n.			2F
Details of the test results related to each specimen can be seen in the annex of this test report.			

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 003900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com



LAB N° 0045 L

Test Report No.: **2307531-001**

Test	Method	U.M.	Result
------	--------	------	--------

The Laboratory Manager

Fausto Albonico

END OF REPORT

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.