



Report VN736 139384.1

Test Report

Applicant

ENGLISCH DEKOR HandelsGmbH & CoKG
Scheydgasse 29
1210-Wien
Austria

Reference

Mrs. Manuela Schopper

Application

Determination of ignitability according to EN 1021 part 1 and part 2.

Test material

„jazz“

Material used in testing was anonymized for laboratory purposes. A detailed sample list is contained in the report.

Issuing and Signatures

Number of pages contained: 5
Original Issue / Vienna 26.03.2018 / AA
Translation

Authorised for Institute
Ing. Hannes Vittek

A handwritten signature in blue ink, appearing to read "i.v. Zwick", written over a dotted line.

Contents

1	Order	2
1.1	Chronology	2
2	Findings / Tests performed.....	2
2.1	Description of the specimen	2
2.2	Assessment of the ignitability of upholstered furniture, Part 1: Ignition source: smouldering cigarette	3
2.3	Assessment of the ignitability of upholstered furniture, Part 2: Ignition source: Gasflame comparable to a matchstick.....	4
3	Remarks	5

1 Order

1.1 Chronology

Date	Received	Order
08.03.2018	09.03.2018	Determination of ignitability according to EN 1021 part 1 and part 2.

2 Findings / Tests performed

2.1 Description of the specimen

Description of the specimen according to DIN 60 000*

Test results

Tested sample: 1

Material composition (declaration by the applicant)	100% Polyester
Technological description	Woven fabric coated on back side

2.2 Assessment of the ignitability of upholstered furniture, Part 1: Ignition source: smouldering cigarette

Test conditions

According to: EN 1021-1

Kind of upholstery: manufactured upholstery

Sample composition

- Outer layer (upholstery fabric): Sample 1

- Filling (stuffing): Polyurethane foam „RF5560“, Producer: Eurofoam,
Burning behaviour: "schwerbrennbar" according to ÖNORM A 3800-1

Pretreatment: Water soaking procedure according EN 1021-1, Annex D

Test results

Tested sample: 1

Inflammation through progressing smouldering	test	
	1	2
specimen displays escalating smouldering combustion behaviour so that it is unsafe to continue the test and forcible extinction is required	no	no
specimen smoulders until it is essentially consumed within the duration of the test	no	no
specimen smoulders to the extremities of the specimen, i.e. to either side or to/through the full thickness of the specimen	no	no
specimen smoulders longer than 60 min after ignition of the cigarette	no	no
Specimen shows evidence of active smouldering on final examination	no	no

Inflammation through burning	test	
	1	2
appearance of flames	no	no

Overall result: No ignition

Note

The test results mentioned above relate only to the ignitability of the combination of upholstery composites under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

2.3 Assessment of the ignitability of upholstered furniture, Part 2: Ignition source: Gasflame comparable to a matchstick

Test conditions

According to: EN 1021-2

Kind of upholstery: manufactured upholstery

Sample composition

- Outer layer (upholstery fabric): Sample 1

- Filling (stuffing): Polyurethane foam „RF5560“, Producer: Eurofoam,
Burning behaviour: "schwerbrennbar" according to ÖNORM A 3800-1

Pretreatment: Water soaking procedure according EN 1021-2, Annex D

Test results

Tested sample: 1

Inflammation through progressing smouldering	1	test 2	3
Specimen displays escalating smouldering combustion behaviour so that it is unsafe to continue the test and forcible extinction is required	no	no	no
Specimen smoulders until it is essentially consumed within the duration of the test	no	no	no
Specimen smoulders to the extremities of the specimen, i.e. to either side or to/through the full thickness of the specimen	no	no	no
Specimen smoulders longer than 60 min after ignition of the cigarette	no	no	no
Specimen shows evidence of active smouldering on final examination	no	no	no

Inflammation through burning	1	test 2	3
Specimen displays escalating combustion behaviour so that it is unsafe to continue the test and forcible extinction is required	no	no	no
Specimen burns until it is essentially consumed within the duration of the test	no	no	no
Specimen on which any flame front reaches the extremities of the specimen other than the top of the vertical part of the test specimen, or passes through the full thickness of the specimen within the duration of the test	no	no	no
Specimen that continues to flame for more than 120 s after removal of the burner tube	no	no	no

Overall result: No ignition

Note

The test results mentioned above relate only to the ignitability of the combination of upholstery composites under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

3 Remarks

Validity

There are no regulations concerning duration of validity in the individual test standards. As the results of the examinations refer only to the submitted and examined samples, the report is valid for these for an unlimited period. A period of validity specified as part of an expert evaluation is in the discretion of the consultant or the ÖTI.

The applicability of results and expert evaluations for materials not tested is in the responsibility of the applicant. Whereby an apportionment of results as well as any specified period of validity can only be done for identically constructed products and only as long as the product produced unchanged.

Possible national or international restrictions concerning the terms of usability of test and classification reports have to be considered; this is not the responsibility of the test laboratory.

Sample Material

Results of performed tests only refer to the sample material provided.

Without explicit written other agreement testing is destructive and the sample material is transferred to the property of ÖTI, which is entitled to freely decide on storage and disposal.

Issuance

The valid first issue is done in paper and has single-handed signatures. For reference purposes and filing an unsigned electronic duplicate can be delivered in pdf format. Duplicates and translations will be marked accordingly on the cover sheet.

Quality management, Accreditation and Notification

All tests and services are performed under a quality management system according to EN ISO/IEC 17025 respectively EN ISO/IEC 17065.

The ÖTI is accredited as Testing Laboratory and Certification Body for products. It also is a Notified Body for several directives with the registration number 0534 (see <http://ec.europa.eu/enterprise/newapproach/hando/>). Accreditation as Testing Laboratory was provided by Akkreditierung Austria (bmwfw). The scope of accreditation is listed on www.bmwfw.gv.at/akkreditierung.

In this report individual non-accredited test procedures are marked with *.

According to the decree on the use of the accreditation mark ("AkkZV") the accreditation mark is only to be used by the accredited Conformity Assessment Body.

Application of the registration number of the Notified Body: As to personal protective equipment (PPE) the requirements of PSA-SV § 10, BGBl. Nr. 596/1994 as amended and article 13 of the Directive 89/686/EEC have to be kept. With construction products the application is only permitted within the declaration of performance for CE-marking.

Copyright and Usage Notes

It is pointed out, that any alterations, amendments or falsifications of reports not authorized by the issuer of the report will be prosecuted as civil and criminal offences; this especially to the appropriate requirements of ABGB, UrhG, UWG and criminal law and their respective international equivalents.

Reports are protected under international copyright laws. Written consent of the ÖTI is required for publications (also in excerpt) and reference to tests for public relation purposes. Reports may only be reproduced in full length.

End of report