
FLAMMABILITY TEST CERTIFICATE - 66148

COMPANY DETAILS: ENGLISH DEKOR HANDEL GesmbH & Co KG
SCHEYDGASSE 29, 1210 WIEN
OSTERREICH

DATE RECEIVED: 16/03/2018
DATE TESTED: 26/03/2018
DATE ISSUED: 26/03/2018
PO NUMBER:

SAMPLE DESCRIPTION: PFP BLACKOUT
COLOUR: WHITE
QUALITY/BATCH REF:
MODEL REF: H8000-H8999, V7516-V7546

COMPOSITION: 100% POLYESTER
SAMPLE END USE: NOT STATED
MANUFACTURER: NOT STATED
SUPPLIER/BUYER: NOT STATED

REQUIRMENT/CLASSIFICATION:

BS EN 13773: 2003 – Textiles and textile products – Burning behaviour – Curtains and drapes classification scheme

TEST METHODS: (Non UKAS Accredited)

BS EN 1101: 1996 – Burning behaviour of curtains & drapes. Detailed procedure to determine the ignitibility of vertically orientated specimens (Small flame)

BS EN 13772: 2011 – Textiles and textile products – Burning behaviour – Curtains & Drapes – Measurement of flame spread of vertically oriented specimens with large ignition source

PRE-TREATMENT:

One set of specimens had been subjected to 5 wash cycles in accordance with BS EN ISO 6330: 2000 Procedure 2A, then line dried.

CONDITIONING:

The sample was conditioned for at least 24 hrs in a specified atmosphere at $20 \pm 2^{\circ}\text{C}$ and $65 \pm 5\% \text{ r h}$.

Authorised By:



Zeb Alam
Operations Director

Mark Jones
Quality Manager

Karen Brooks
Managing Director

Please note: The test(s) carried out is a non UKAS accredited test, all results issued on this certificate refer only to the item tested and therefore doesn't relate to the lot or batch of the product / sample. This test certificate shall not be duplicated. Textile Innovation House, 1 Lyons Road, Trafford Park, Manchester, M17 1RN. T: 0161 50 50 650 E: technical@ifs-labs.com

FLAMMABILITY TEST CERTIFICATE – 66148

TEST RESULTS: BS EN 1101: 1996

TEST NUMBER	FLAME APPLICATION TIME	RESULT	TEST NUMBER	FLAME APPLICATION TIME	RESULT
1	1s	No Ignition	7	15s	No Ignition
2	2s	No Ignition	8	20s	No Ignition
3	3s	No Ignition	9	20s	No Ignition
4	4s	No Ignition	10	20s	No Ignition
5	5s	No Ignition	11	20s	No Ignition
6	10s	No Ignition	12	20s	No Ignition

TEST RESULTS: BS EN 13772: 2011

Test Criteria BEFORE CLEANSING

	1	2	3	4	5	6
Specimen Direction:	↑	↓	↑	←	→	←
Application Time:	10	10	10	10	10	10
Flaming Duration:	4.6	11.6	3.2	5.1	4.4	3.6
1 st Marker thread (Sec)	NS	NS	NS	NS	NS	NS
2 nd Marker thread (Sec)	NS	NS	NS	NS	NS	NS
Time to sever 3 rd Marker thread (Sec)	NS	NS	NS	NS	NS	NS
Flaming Debris	N	N	N	N	N	N
Damage Length: (mm)	164	159	160	161	157	153
Result	PASS	PASS	PASS	PASS	PASS	PASS

Test Criteria AFTER CLEANSING

	1	2	3	4	5	6
Specimen Direction:	↑	↓	↑	←	→	←
Application Time:	10	10	10	10	10	10
Flaming Duration:	3.1	5.4	5.6	4.2	3.1	3.0
1 st Marker thread (Sec)	NS	NS	NS	NS	NS	NS
2 nd Marker thread (Sec)	NS	NS	NS	NS	NS	NS
Time to sever 3 rd Marker thread (Sec)	NS	NS	NS	NS	NS	NS
Flaming Debris	N	N	N	N	N	N
Damage Length: (mm)	167	163	165	171	164	166
Result	PASS	PASS	PASS	PASS	PASS	PASS

KEY: N = NO Y = YES NS = Not Severed

CONCLUSION:

The sample supplied has achieved a class 1 in accordance with BS EN 13773: 2003

END OF REPORT

Please note: The test(s) carried out is a non UKAS accredited test, all results issued on this certificate refer only to the item tested and therefore doesn't relate to the lot or batch of the product / sample. This test certificate shall not be duplicated. Textile Innovation House, 1 Lyons Road, Trafford Park, Manchester, M17 1RN. T: 0161 50 50 650 E: technical@ifs-labs.com