

FLAMMABILITY TEST REPORT

Report No.: LEI23070145A
Original

Date Received: 30/06/23

Date Tested: 06/06/23

Date Issued: 06/06/23

Company Name & Address: ENGLISCH DEKOR
SCHEYDGASSE 29
AT-1210 WIEN

Contact Name: MS. KIM VILLALUZ

Sample Details

Order No.: Not stated
Description: Not stated
Style No.: Not stated
Batch No.: Not stated
Quality: "lanchester"
Colour: Not stated
Supplier: Not stated
End Use: Upholstery fabric
Quoted Fibre Composition: 13% CO, 37% MAC, 50% PES FR
Retailer: Not stated
Buying Division: Not stated
Sample Description: Green coloured fabric

Test Method	Pre Treatment	Flammability Performance Requirements	Result
IMO FTP Code (2010) – Annex 1, Part 8 (Smouldering cigarette test)	None	IMO FTP Code (2010) – Annex 1, Part 8	PASS
IMO FTP Code (2010) – Annex 1, Part 8 (Propane flame test)	None	IMO FTP Code (2010) – Annex 1, Part 8	PASS

.....
STEVEN OWEN
(Technical & Operational Excellence Manager)


.....
ANDREW HALLETT
(Flammability Team Leader)

.....
CAROLE SPOWART
(Flammability Administrator)

.....
GREGORY JAMES
(Flammability Technician)

Additional Information (Annex)

Name and Address of the Sponsor: Not stated
Name and Address of the Manufacturer/Supplier (If known): Not stated
Type of Furniture: Upholstery fabric
Fabric Details – Weave/Density/Yarn count/thickness(mm)/mass(g/m²) Colour & Tone: Not stated
Fire Retardant Treatment: Yes

Uncertainty of Measurement

The uncertainty of measurement for Ignition source 0 has been estimated to be 0.03%
The uncertainty of measurement for Ignition source 1 has been estimated to be 5.43%

Test Specification

Test Method: IMO FTP Code (2010) – Annex 1, Part 8
Ignition Source: Ignition source 0: Filterless cigarette
Ignition source 1: Propane Gas (95% Purity) flowing at 6.38±0.25 g/hour @ 20°C.
Flame Application Time: 20±1 seconds
Side Tested: Face

Cigarette Specification

Cigarette Type: Filterless cigarette
Dimensions: Length: 70±4 mm
Diameter: 8±0.5 mm
Mass: 0.95±0.15 g
Smouldering Rate: 11±4.0 min/50mm

Filling Specification

Filling Type: Polyurethane Foam
Supplier / Grade: Carpenter / RP21130 Unmodified
Size: 450 X 300 X 75mm (back) & 450 X 150 X 75mm (seat)
Density / Hardness: 20-22 kg/m³ / Type B, 130N

Pre-treatment / Durability procedure

None. Tested as received

Conditioning

Prior to Testing: At least 72 hours in ambient indoor conditions, then at least 16 hours in an atmosphere having a temperature of 23±2°C and a relative humidity of 50±5%
At Time of Testing: Temperature between 15°C & 25°C. Relative humidity between 20% & 70%

Test Results

"The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use."

Cigarette Test	Initial		Repeat	
Criterion of Ignition				
Smoulders More Than 1 Hour	No		No	
In Final Examination, Presence of Active Smouldering	No		No	
Occurrence Of Flames	No		No	
Comments				
Flaming Ceased	-		-	
Glowing Ceased	-		-	
Smoke Ceased	The cigarette failed to burn its complete length, there was no flaming or progressive smouldering		The cigarette failed to burn its complete length, there was no flaming or progressive smouldering	
Extent of Damage (Burning and/or Charring)				
Damage to Back (mm) Length / Width	-	-	-	-
Damage to Base (mm) Length / Width	-	-	-	-
Result	PASS		PASS	

Propane Flame Test	Initial		Repeat	
Criterion of Ignition				
Smoulders More Than 1 Hour	No		No	
In Final Examination, Presence of Active Smouldering	No		No	
Flames For Longer Than 120 Seconds	No		No	
Comments				
Flaming Ceased	0 Seconds		0 Seconds	
Glowing Ceased	-		-	
Smoke Ceased	17 Seconds		14 Seconds	
Extent of Damage (Burning and/or Charring)				
Damage to Back (mm) Length / Width	50	15	80	17
Damage to Base (mm) Length / Width	10	13	12	11
Result	PASS		PASS	

Conclusions

When tested over RP21130 foam) the sample meets the flammability performance requirements of the smouldering cigarette test in FTP Code (2010) – Annex 1, Part 8. **PASS.**

When tested over RP21130 foam the sample meets the flammability performance requirements of the propane flame test in FTP Code (2010) – Annex 1, Part 8. **PASS.**

The client acknowledges and agrees that any services provided and/or reports produced by Intertek are done so within the limits of the scope of work agreed pursuant to the client's specific instructions. This report relates specifically to the sample(s) tested that were drawn and delivered by the client or their nominated third party. Intertek does not make any representation or warranty for any bulk samples or certify the bulk samples received from the client. Furthermore, Intertek does not provide a warranty or verification on the sample(s) representing any specific goods, material and/or shipment and only relate to the sample(s) as received and tested. Intertek have aimed to conduct the review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. In no event, will the contents of any reports or any extracts, excerpts or parts of any reports be distributed or published without the prior written consent of Intertek in each instance. Only the client is authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.

The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor of $k = 2$, providing a level of confidence of approximately 95 %. Unless otherwise specified all compliance and pass/fail statements are binary simple acceptance based on the tolerance interval and, with the exception of graded methods, a test uncertainty ratio greater (TUR) than 4:1. For graded methods the TUR will drop to as low as 0.5:1 when the tolerance limits are within a grade division of the upper scale limit. The Uncertainty budgets are stated for each Test method, these are for reference, and should be considered when results are on or close to Specification Limits / Requirements and in such cases it should be noted that the risk of false acceptance or rejection may be as high as 50%, for further information please refer to ILAC G8.