

FLAMMABILITY TEST REPORT

Report No.: LEHTX00909300
Retype

Date Received: 15/09/16

Date Tested: 21/09/16

1st Date Issued: 22/09/16

Retype Issued: 26/07/18

Company Name & Address: ENGLISCH DEKOR
SCHEYDGASSE 29
AT-1210 WIEN

Contact Name: MANUELA SCHOPPER

Sample Details

Reference No.: Not stated
Order No.: Not stated
Style No.: Not stated
Batch No.: Not stated
Quality: Touch + Touch basic
Colour: Not stated
Supplier: Not stated
Intended Use: Upholstery
Quoted Fibre Composition: 100% PU + Backing
Retailer: Not stated
Sample Description: White coloured material with brown coloured coating

Test Method	Pre Treatment	Flammability Performance Requirements	Result
IMO FTP Code (2010) – Annex 1, Part 8 (Smouldering cigarette test)	None	IMO FTP Code (2010) – Annex 1, Part 8	PASS
IMO FTP Code (2010) – Annex 1, Part 8 (Propane flame test)	None	IMO FTP Code (2010) – Annex 1, Part 8	PASS
Please note: The fabric was tested over a non-flame-retardant filling (RP21130) as suggested in Appendix 3 of the IMO FTP Code 2010.			

STEVEN OWEN
(Chemical Technologist)

ANDREW HALLETT
(Flammability Team Leader)

CAROLE SPOWART
(Flammability Technician)

SIMON CHEE
(Operations Manager)

Report No.: LEHTX00909300 Retype Page 1 of 3

FLAMMABILITY TEST REPORT

Additional Information (Annex)

Name and Address of the Sponsor: Not Stated
Name and Address of the
Manufacturer/Supplier (If known): Not Stated
Type Of Furniture: Not Stated
Fabric Details – Weave/Density/Yarn
count/thickness(mm)/mass(g/m²)Colour &
Tone: Not Stated
Fire Retardant Treatment: Yes

Test Specification

Test Method: IMO FTP Code (2010) – Annex 1, Part 8
Ignition Source: Ignition source 0: Calibrated Senior Service cigarette
Ignition source 1: Propane Gas (95% Purity) flowing at 6.38±0.25 g/hour @ 20°C.
Flame Application Time: 20±1 seconds
Side Tested: Face

Cigarette Specification

Cigarette Type: Calibrated Senior Service cigarette
Dimensions: Length: 70±4 mm
Diameter: 8±0.5 mm
Mass: 0.95±0.15 g
Smouldering Rate: 11±4.0 min/50mm

Filling Specification

Filling Type: Polyurethane Foam
Supplier / Grade: Carpenter / RP21130 unmodified
Size: 450 X 300 X 75mm (back) & 450 X 150 X 75mm (seat)
Density / Hardness: 20-22 kg/m³ / Type B, 130

Pre-treatment / Durability procedure

None. Tested as received

Conditioning

Prior to Testing: At least 72 hours in ambient indoor conditions, then at least 16 hours in an
atmosphere having a temperature of 23±2°C and a relative humidity of 50±5%
At Time of Testing: Temperature between 15°C & 25°C. Relative humidity between 20% & 70%

FLAMMABILITY TEST REPORT

Test Results

"The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use."

Cigarette Test	Initial		Repeat	
Criterion of Ignition				
Smoulders More Than 1 Hour	No		No	
In Final Examination, Presence of Active Smouldering	No		No	
Occurrence Of Flames	No		No	
Comments				
Flaming Ceased	-		-	
Glowing Ceased	-		-	
Smoke Ceased	The cigarette failed to burn its complete length		The cigarette failed to burn its complete length	
Extent of Damage (Burning and/or Charring)				
Damage to Back (mm) Length / Width	-	-	-	-
Damage to Base (mm) Length / Width	-	-	-	-
Result	PASS		PASS	

Propane Flame Test	Initial		Repeat	
Criterion of Ignition				
Smoulders More Than 1 Hour	No		No	
In Final Examination, Presence of Active Smouldering	No		No	
Flames For Longer Than 120 Seconds	No		No	
Comments				
Flaming Ceased	0 Seconds		0 Seconds	
Glowing Ceased	12 Seconds		21 Seconds	
Smoke Ceased	18 Seconds		24 Seconds	
Extent of Damage (Burning and/or Charring)				
Damage to Back (mm) Length / Width	65	14	85	14
Damage to Base (mm) Length / Width	11	10	11	10
Result	PASS		PASS	

Conclusions

When tested over a non-flame-retardant filling (RP21130) as suggested in Appendix 3 of the IMO FTP Code 2010 the sample meets the flammability performance requirements of the smouldering cigarette test in IMO FTP Code (2010) – Annex 1, Part 8. **PASS.**

When tested over a non-flame-retardant filling (RP21130) as suggested in Appendix 3 of the IMO FTP Code 2010 the sample meets the flammability performance requirements of the propane flame test in IMO FTP Code (2010) – Annex 1, Part 8. **PASS.**

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.