



LANARTEX S.r.l.

Via I Maggio, 27
59013 Oste - Montemurlo (PO)
Tel.: 0574-071701 Fax: 0574-899903
E-mail: labo@lanartex.it
www.lanartex.it



LAB N° 0572 L

MESSRS:

ENGLISH DEKOR HANDELSGMBH & CO KG

SCHEYDGASSE 29
1210 WIEN (AUSTRIA)
AT

REPORT NR

250006028-001

REPORT DATE

09/09/2025

ACCEPTANCE DATE

08/09/2025

START TEST DATE

09/09/2025

END TEST DATE

09/09/2025

SAMPLING BY CUSTOMER

TEST REPORT

Item Name: ART. AQUATEX SOFT

Material type: Orthogonal fabric

Intended use: Upholstery

Technical Manager

Dott.ssa Guidotti Valentina

Manager Director

Patrizia Rosati

(*) = Tests and analytes marked with asterisk are not accredited ACCREDIA. The content of the present document refers **exclusively to the submitted samples** and not to the batch that they want to represent. This report is made solely on the basis of materials supplied by the customer. This test report cannot be reproduced in part without written permission of LANARTEX. The sample description content is under the full responsibility of the customer and not of the laboratory. Except when specifically stated, **the results apply to the sample as received**. For any further information, please read the General Sales Condition on the Lanartex website.



LANARTEX S.r.l.

Via I Maggio, 27
59013 Oste - Montemurlo (PO)
Tel.: 0574-071701 Fax: 0574-899903
E-mail: labo@lanartex.it
www.lanartex.it



LAB N° 0572 L

REPORT NR
REPORT DATE

250006028-001
09/09/2025

TEST LIST

TEST

METHOD

ACCREDIA

Water Resistance - Hydrostatic Pressure Test

Resistenza all'acqua - Prova sotto pressione idrostatica

UNI EN ISO 811:2018

(*) = Tests and analytes marked with asterisk are not accredited ACCREDIA. The content of the present document refers **exclusively to the submitted samples** and not to the batch that they want to represent. This report is made solely on the basis of materials supplied by the customer. This test report cannot be reproduced in part without written permission of LANARTEX. The sample description content is under the full responsibility of the customer and not of the laboratory. Except when specifically stated, **the results apply to the sample as received**. For any further information, please read the General Sales Condition on the Lanartex website.



LANARTEX S.r.l.

Via I Maggio, 27
59013 Oste - Montemurlo (PO)
Tel.: 0574-071701 Fax: 0574-899903
E-mail: labo@lanartex.it
www.lanartex.it



LAB N° 0572 L

REPORT NR
REPORT DATE

250006028-001
09/09/2025

RESULTS

	M.U.	RESULT
UNI EN ISO 811:2018		
Water Resistance - Hydrostatic Pressure Test		
<i>Resistenza all'acqua - Prova sotto pressione idrostatica</i>		
Application side		Face side
<i>Lato di applicazione</i>		Diritto
Water temperature		20
<i>Temperatura dell' acqua</i>	°C	
End of test		Water penetration occurs in three places of the fabric
<i>Termine prova</i>		L'acqua penetra nel terzo punto del tessuto
Specimen 1		494
<i>Provino 1</i>	cmH ₂ O	
Specimen 2		460
<i>Provino 2</i>	cmH ₂ O	
Specimen 3		484
<i>Provino 3</i>	cmH ₂ O	
Specimen 4		552
<i>Provino 4</i>	cmH ₂ O	
Specimen 5		490
<i>Provino 5</i>	cmH ₂ O	
Mean		496.0
<i>Media</i>	cmH ₂ O	

NOTES

The specimens have been acclimatized and the test performed in atmosphere to 20±2°C and 65±4%RH in compliance with norm UNI EN ISO 139 (standard atmosphere). Instrument: Water Proof 355 for recording water penetration resistance by electronic reading. Rate of increase of water pressure: 60 cmH₂O/min. The water pressure is applied from below above the test specimen. During the test impregnation of the sample is observed due to its particular conformation, it is therefore not possible to continue with the test, so an indicative data is reported. The laboratory declines all responsibility in this regard.

I campioni da testare sono stati ambientati e la prova eseguita a 20±2°C e 65±4%UR conformemente alla norma UNI EN ISO 139 (atmosfera standard). Strumento: Water Proof 355 per registrazione resistenza alla penetrazione dell'acqua con lettura elettronica. Incremento della pressione dell'acqua: 60 cmH₂O/min. La pressione dell'acqua viene applicata al di sotto del provino. Durante la prova si osserva impregnazione del campione a causa della sua particolare conformazione, non è pertanto possibile proseguire con il test, per cui viene riportato un dato orientativo. Il laboratorio declina ogni responsabilità in merito.

END OF REPORT

(*) = Tests and analytes marked with asterisk are not accredited ACCREDIA. The content of the present document refers **exclusively to the submitted samples** and not to the batch that they want to represent. This report is made solely on the basis of materials supplied by the customer. This test report cannot be reproduced in part without written permission of LANARTEX. The sample description content is under the full responsibility of the customer and not of the laboratory. Except when specifically stated, **the results apply to the sample as received**. For any further information, please read the General Sales Condition on the Lanartex website.